

Polyamide 6

Product description

Unreinforced, toughened, PA6, performance polyamide
SenTherm 301-01 2 is a high-performance thermally conductive, electrically isolative resin for injection moulding

Product applications

SenTherm 301-01 2 is an advanced thermoplastic polyamide, utilising novel fillers for applications in EV cars. This polymer can be used in battery spacers, battery closures and other electrical components. This polymer meets the demand of lightweight and lower embodied carbon.

Product Information

Resin Identification	PA6	ISO 1043
----------------------	-----	----------

Rheological properties¹⁾

Properties	Method	Unit	Typical Value*
<i>Mould shrinkage, parallel ²⁾</i>	<i>ISO 294-4, 2577</i>	<i>%</i>	<i>0.5</i>
<i>Mould shrinkage, transversal ²⁾</i>	<i>ISO 294-4, 2577</i>	<i>%</i>	<i>0.6</i>

Characteristics ¹⁾

Properties	Method	Unit	Typical Value*
Density	ISO 1183	Kg/m ³	1480
<i>Melt flow rate 275°C @ 5kg</i>	<i>ISO1133/T</i>	<i>g/10 min</i>	<i>5</i>
Thermal conductivity (Injection moulded)	ASTM D7984	W/mK	1.5
Thermal conductivity (Compression moulded)	ASTM D7984	W/mK	2.8
Tensile modulus	ISO 527	MPa	-
Tensile strength	ISO 527	MPa	-
Strain at break	ISO 527	%	-

*Values in italics are estimated

Characteristics ¹⁾

Properties	Method	Unit	Typical Value*
Flexural modulus	ISO 178	MPa	-
Charpy impact (23°C)	ISO 180/1A	kJ/m ²	-

Injection ¹⁾

Properties	Unit	Typical Value*
Drying recommended		Yes
Drying temperature	°C	80
Drying time, dehumidified oven	Hours	4
Process moisture content	%	0.1
Melt temperature	°C	260
Min melt temperature	°C	250
Max melt temperature	°C	270
Min mould temperature	°C	70
Max mould temperature	°C	90
Ejection temperature	°C	180

- 1) The information stated on technical data sheets should be used as indicative only for material selection and not utilised for specifications or part and tool design.
- 2) Measurements have been estimated from moulded laboratory parts; actual shrinkage may be outside these parameters. This is dependant on mould conditions and parameters. Our recommendation is using legacy tooling before cutting on a new moulding tool.

Disclaimer

The information provided in this document is given in good faith and is believed to be accurate and to the best of our knowledge at the time of publication. However, SenTherm makes no representations or warranties, express or implied, regarding the accuracy, completeness, or reliability of the information contained herein. All values stated are typical and should not be considered as specification limits. Actual values may vary.

SenTherm assumes no liability for the use, processing, or application of this material. It is the responsibility of the buyer to conduct independent testing and evaluation to determine the suitability of the material for its intended use. No information contained herein should be construed as granting any licence or right under any patent or intellectual property. No statement regarding potential applications of the material, which is patent pending, shall be interpreted as an inducement to infringe any patents. To the utmost extent permitted by law, SenTherm disclaims all liability for any direct, indirect, incidental, or consequential damages arising from the use of this information or the material described.